

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

AcN 2636

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C07C 407/00, 409/38, 409/40, C08F 4/36, 299/04		A1	(11) International Publication Number: WO 99/52864 (43) International Publication Date: 21 October 1999 (21.10.99)
(21) International Application Number: PCT/EP99/02643 (22) International Filing Date: 13 April 1999 (13.04.99) (30) Priority Data: 98201170.2 15 April 1998 (15.04.98) EP (71) Applicant (for all designated States except US): AKZO NOVEL N.V. [NL/NL]; Velperweg 76, NL-6824 BM Arnhem (NL). (72) Inventors; and (75) Inventors/Applicants (for US only): VAN DE BOVENKAMP-BOUWMAN, Anna, Gerdine [BE/NL]; Appelsestraat 12, NL-3862 PH Nijkerk (NL); VAN GENDT, Joachim, Willem, Joseph [NL/NL]; Holteveenseweg 4, NL-8105 SW Luttenberg (NL). MEIJER, John [NL/NL]; R. Heyligersstraat 18, NL-7415 ES Deventer (NL). FISCHER, Bart [NL/NL]; Bitterschoten 42, NL-3831 PC Leusden (NL). HOGT, Andreas, Herman [NL/NL]; Deurningerstraat 58, NL-7514 BJ Enschede (NL). (74) Agent: SCHALKWIJK, Pieter, Cornelis; Akzo Nobel N.V., Patent Dept. (Dept. APTA), P.O. Box 9300, NL-6800 SB Arnhem (NL).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>	
(54) Title: PEROXIDES, THEIR PREPARATION PROCESS AND USE			
(57) Abstract The invention relates to the preparation process of peroxy esters and peroxy carbonates, peroxy ester peroxy carbonates, mixed diperoxides, mixed diperoxy esters, and mixed diperoxy carbonates, and to specific monoperoxy esters, monoperoxy carbonates, mixed peroxides, mixed diperoxy esters, mixed diperoxy carbonates, peroxy ester peroxy carbonates, and mixtures thereof. The process involves the reaction of a type-3 ketone peroxide with a reactive carbonyl compound and optional subsequent reaction with an alkyl vinyl ether, acetal, halogen formate, or carboxylic acid anhydride.			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

PEROXIDES, THEIR PREPARATION PROCESS AND USE

5 The present invention relates to particular peroxides, mixtures comprising one or more of these peroxides, their preparation process, and their use. More particularly, the present invention relates to the preparation process of peroxy esters and peroxy carbonates, peroxy ester peroxy carbonates, mixed diperoxides, mixed diperoxy esters, and mixed diperoxy carbonates, and to
10 specific monoperoxy esters, monoperoxy carbonates, mixed peroxides, mixed diperoxy esters, mixed diperoxy carbonates, peroxy ester peroxy carbonates, and mixtures thereof. Finally, the present invention relates to the use of these peroxides as polymerization initiators, curing agents for unsaturated polyesters, and modifying agents, and to formulations comprising these peroxides.

15 JP-A-50-23079 discloses the production of symmetric peroxides by reacting a dialkyl ketone hydroperoxyde with an acyl chloride in a two-phase solvent system comprising a polar (aqueous) solvent and an apolar solvent. A monoperoxy ester or monoperoxy carbonate is not formed. The peroxy esters are used in the homopolymerization of ethylene or the copolymerization of
20 ethylene and another ethylenically unsaturated monomer.

JP-A-48-43491 discloses a similar method for the production of diperoxy carbonates.


Because these prior art preparation processes do not result in the formation of monoperoxy ester or monoperoxy carbonate as a major constituent, it is not
25 possible to produce asymmetric diperoxy esters, diperoxy carbonates, and mixed peroxides in a controlled manner.

It is an object of the present invention to provide a new class of monoperoxy esters and monoperoxy carbonates which on the one hand are useful as polymerization initiators, curing agents for unsaturated polyesters, and
30 modifying agents, and on the other serve as a starting material for the production of a novel class of mixed peroxides, mixed diperoxy esters, mixed diperoxy carbonates, and peroxy ester peroxy carbonates which are also useful


as polymerization initiators, curing agents for unsaturated polyesters, and modifying agents.

The present invention is based on the insight that by the proper selection of ketone peroxides on the one hand and acid halogen or halogen formate on the other, monoperoxy esters and monoperoxy carbonates are formed in an adjustable relative amount. These monoperoxy esters and monoperoxy carbonates in turn allow the provision of a new class of mixed peroxides, mixed diperoxy esters, mixed diperoxy carbonates, and peroxy ester peroxy carbonates.

Accordingly, the present invention provides a process for the preparation of monoperoxy ester or monoperoxy carbonate having the general formula I:



wherein R_1 and R_2 are independently selected from the group comprising hydrogen, $\text{C}_1\text{-C}_{20}$ alkyl, $\text{C}_3\text{-C}_{20}$ cycloalkyl, $\text{C}_6\text{-C}_{20}$ aryl, $\text{C}_7\text{-C}_{20}$ aralkyl, and $\text{C}_7\text{-C}_{20}$ alkaryl, or R_1 and R_2 form a $\text{C}_3\text{-C}_{12}$ cycloalkyl group, which groups may include linear or branched alkyl moieties, and each of R_1 and R_2 may optionally be substituted with one or more groups selected from hydroxy, alkoxy, linear or branched alkyl, aryloxy, halogen, ester, carboxy, nitrile, and amido, and R_3 is independently selected from the group comprising $\text{C}_1\text{-C}_{20}$ alkyl, $\text{C}_3\text{-C}_{20}$ cycloalkyl, $\text{C}_6\text{-C}_{20}$ aryl, $\text{C}_7\text{-C}_{20}$ aralkyl, and $\text{C}_7\text{-C}_{20}$ alkaryl, which groups may include linear or branched alkyl moieties, and R_3 may optionally be substituted with one or more groups selected from hydroxy, alkoxy, linear or branched alkyl, aryloxy, halogen, ester, carboxy, nitrile, and amido, which process comprises the reaction of the corresponding ketone peroxide with the general formula II:



wherein R_1 and R_2 have the identified meaning, with a reactive carbonyl compound with the general formula III:



wherein R_3 has the identified meaning and L is a group activating a carbonyl group of the carbonyl compound (III) for reaction with the ketone peroxide (II), in an inert two-phase solvent system comprising a polar solvent and an apolar solvent. Ketone peroxides of formula II are also known as type-3 (T3) ketone peroxides.

The inert two-phase solvent system comprises a polar solvent and an apolar solvent. Preferably the polar solvent is an aqueous alkali comprising phase. The apolar solvent is not miscible with the polar solvent. A solvent is a polar solvent when its dipole moment is larger than 0D, and preferably larger than 0.5D, in other words, when it has a certain polarity. A solvent is an apolar solvent when its dipole moment is 0.5D or less, preferably essentially 0D. The apolar solvent has substantially no polarity.

Suitable polar solvents comprise alcohols, cycloalkanols, ethers, alkylene glycols, amides, aldehydes, ketones, esters, halogenated hydrocarbons such as chlorinated hydrocarbons, and mixtures thereof. The use of polar solvents like anhydrides, carbonates, and epoxides is less desired since they are not fully inert.

However, an aqueous (alkali) phase is preferred as the polar solvent.

Suitable apolar solvents generally are hydrocarbon solvents, aromatic hydrocarbon solvents, aralkyl solvents, paraffinic oils, white oils, and silicone oils, as well as their mixtures. Useful hydrocarbon solvents include, but are not limited to, benzene, xylene, toluene, mesitylene, hexane, hydrogenated oligomers of alkanes such as Isopar^R products (ex. Exxon), Shellsol^R products (ex Shell), pentane, heptane, decane, isododecane, decalin, and the like. Paraffinic oils useful as apolar solvents comprises for instance paraffinic diesel oil. Other oils, including white oils, epoxidized soybean oils, and silicone oils are also useful in the present invention.

By properly selecting the equivalent amount of the carbonyl compound used in the preparation process, the amount of monoperoxy ester and monoperoxy carbonate can be adjusted further. The amounts are preferably selected such that at least 10% by weight of the desired product is formed. More preferably such that at least 25% by weight of these products is formed. Even more preferably, the amount of acid halogen or halogen formate is in the range of 0.5-5 equivalents, so that the amount of monoperoxy ester and monoperoxy carbonate formed is at least 50% of the produced peroxides. Using 0.9-2.5 equivalents the selectivity is increased further. Most preferred is an equivalent amount in the range of 1-2 equivalents. Then the selectivity generally is above 60%, such as above 80% or even above 90%. This selectivity may be expressed in the mono: bis ratio.

The reaction conditions are conventional. The temperature generally is in the range of -10 to 50°C and suitably between 0-30°C. A practical range is from 5 to 15°C. Essentially the temperature is selected such that side reactions and decomposition of the materials are avoided. The pH is basic, i.e. above 7. Generally, the pH is in the range of 9-14. In practice, the pH is above 10, and a practical range is from 11 to 13.5. The reaction proceeds under ambient pressure and in free contact with the atmosphere.

Suitable ketone peroxides for the reaction with the carbonyl compound are those derived from the following ketones: acetone, acetophenone, methyl-n-amyl ketone, ethylbutyl ketone, ethylpropyl ketone, methylisoamyl ketone, methylheptyl ketone, methylhexyl ketone, ethylamyl ketone, diethyl ketone, dipropyl ketone, methylethyl ketone, methylisobutyl ketone, methylisopropyl ketone, methylpropyl ketone, methyl-n-butyl ketone, methyl-t-butyl ketone, isobutylheptyl ketone, diisobutyl ketone, methoxy acetone, cyclohexanone, 2,4,4-trimethyl cyclo hexanone, N-butyllevulinate, ethylacetoacetate, methylbenzyl ketone, phenylethyl ketone, methylchloromethyl ketone, methylbromomethyl ketone, and coupling products thereof. Other ketones having the appropriate R₁ and R₂ groups corresponding to the peroxides of the formula II can also be employed.

L may be any group that activates the carbonyl group of the carbonyl compound for reaction with a hydroperoxide group of the ketone peroxide, and substantially does not interfere with this reaction. Suitable examples of L are halogen and the groups $-O-R_3'$, $-O-CO-R_3'$ and $-O-CO-O-R_3'$. R_3' is selected independently of R_3 from the same group of substituents as R_3 . When L is halogen, the carbonyl compound (III) is an acid halogen or a halogen formate. When L is the group $-O-R_3'$, the carbonyl compound (III) is a carboxylic acid ester or a carbonate. When L is the group $-O-CO-R_3'$, the carbonyl compound (III) is a carboxylic acid anhydride or a mixed anhydride. When L is the group $-O-CO-O-R_3'$ the carbonyl compound (III) is a pyrocarbonate or a mixed anhydride.

Preferred acid halogens comprise those wherein R_3 is a linear or branched C_1 - C_{12} alkyl, cycloalkyl, aryl, aralkyl, alkaryl group, the aryl group preferably being a phenyl group. Typical examples are the acid halogens obtainable from the following carboxylic acids: acetic acid, phenylacetic acid, phenoxyacetic acid, propanoic acid, isobutyric acid, benzoic acid, 2-methyl-benzoic acid, 2-methylbutanoic acid, 2-butenic acid, 3-phenylpropenic acid, 2,2-dimethylpropanoic acid, 2,2-dimethylbutanoic acid, 2,2-dimethylpentanoic acid, 2-ethylbutanoic acid, 3,5,5-trimethylhexanoic acid, 2-ethylhexanoic acid, neohexanoic acid, neoheptanoic acid, neodecanoic acid, octanoic acid, nonanoic acid, lauric acid, 3,5,5-trimethylpentanedioic acid, hexanedioic acid, 3,5,5-trimethylhexanedioic acid, 2,4,4-trimethylhexanedioic acid, decanedioic acid, undecanedioic acid, dodecanedioic acid, cyclohexanecarboxylic acid, 1,4-cyclohexanedicarboxylic acid, cyclohexane-1,4-diacetic acid, maleic acid, citric acid, methylsuccinic acid, citraconic acid, fumaric acid, oxalic acid, terephthalic acid, propenoic acid, and phthalic acid, and their corresponding methyl esters, ethyl esters, n-propyl esters, isopropyl esters, n-butyl esters, sec-butyl esters, isobutyl esters, ethylene glycol esters, and propylene glycol esters. Preferably the halogen is chlorine.

Preferred halogen formates are chloroformates. Examples of the chloroformates used are:

- 2-(1-methylethoxy)phenyl chloroformate, 1-methylpropyl chloroformate, 4-methylphenyl chloroformate, 2,2,2-trichloro-1,1-dimethylethyl chloroformate, heptyl chloroformate, cyclohexylmethyl chloroformate, ethyleneglycol bis(chloroformate), 3-(1,1-dimethylethyl)phenyl chloroformate, 3-
- 5 (trichlorosilyl)propyl chloroformate, phenyl chloroformate, 3-methoxybutyl chloroformate, 2-phenoxyethyl chloroformate, 2,2-dimethyl-1,3-propanediol bis(chloroformate), phenylmethyl chloroformate, 9-octadecenyl chloroformate, 2-methylphenyl chloroformate, bisphenol A bis(chloroformate), 1,3-dimethylbutyl chloroformate, 3,4-dimethylbutyl chloroformate, 3,4-
- 10 dimethylphenyl chloroformate, trichloromethyl chloroformate, 1-chloroethyl chloroformate, chloromethyl chloroformate, 1,4-butanediol bis(chloroformate), 1,1-bis (ethoxycarbo)ethyl chloroformate, 3,5-dimethylphenyl chloroformate, octyl chloroformate, ethyl chloroformate, octadecyl chloroformate, (2-oxo-1,3-dioxolan-4-yl)methyl chloroformate, 1,6-hexanediol bis(chloroformate), 2-
- 15 chlorobutyl chloroformate, 4-methoxyphenyl chloroformate, 2-methylpropyl chloroformate, 2-(methylsulfonyl)ethyl chloroformate, dodecyl chloroformate, 1,4-cyclohexanedimethanol bis(chloroformate), 2-chloro-2-phenylethyl chloroformate, 2-acryloyloxyethyl chloroformate, 4-nitrophenyl chloroformate, n-butyl chloroformate, decyl chloroformate, 2-ethylhexyl chloroformate, 2-
- 20 propenyl chloroformate, 2-chlorocyclohexyl chloroformate, 2-methyl-2-propenyl chloroformate, cyclohexyl chloroformate, 2-chloroethyl chloroformate, [4-(phenylazo)phenyl]methyl chloroformate, hexadecyl chloroformate, 1-naphthalenyl chloroformate, 2-[2-cyclopentyl-4-(1,1-dimethylethyl)phenoxy]-1-methylethyl chloroformate, 3,5,5-trimethylhexyl chloroformate, isotridecyl
- 25 chloroformate, tridecyl chloroformate, 4-(1,1-dimethylethyl)cyclohexyl chloroformate, 2,4,5-trichlorophenyl chloroformate, 3-chloropropyl chloroformate, tetradecyl chloroformate, 9H-fluoren-9-ylmethyl chloroformate, (4-nitrophenyl)methyl chloroformate, methyl chloroformate, 2-(1-methylethyl)phenyl chloroformate, triethyleneglycol bis(chloroformate), 2-
- 30 methoxyethyl chloroformate, 1-methylethenyl chloroformate, 3-methylphenyl chloroformate, 2-bromoethyl chloroformate, diethyleneglycol bis(chloroformate),

3-methyl-5-(1-methylethyl)phenyl chloroformate, 2,2,2-tribromoethyl chloroformate, 2-ethoxyethyl chloroformate, 3-methyl-1,5-pentanediol bis(chloroformate), 4-methoxy carbophenyl chloroformate, ethenyl chloroformate, 1-methylethyl chloroformate, 2-(1-methylpropyl)phenyl chloroformate, 2,2,2-trichloroethyl chloroformate, pentyl chloroformate, cyclodecyl chloroformate, 4-(1,1-dimethylethyl)phenyl chloroformate, hexyl chloroformate, n-propyl chloroformate, 3-methoxy-3-methylbutyl chloroformate, 2-propoxyethyl chloroformate, 2-methoxy-1-methylethyl chloroformate, 2-butoxyethyl chloroformate, 2,2-dimethylpropyl chloroformate, 2,3-dihydro-2,2-dimethyl-7-benzofuranyl chloroformate, 1-chloroethyl chloroformate, cyclobutyl chloroformate, 5-methyl-2-(1-methylethyl)cyclohexyl chloroformate, 1,1-dimethylethyl chloroformate, 1-methylheptyl chloroformate.

Suitable carboxylic acid anhydrides or mixed anhydrides are those derived from the carboxylic acids: acetic acid, phenylacetic acid, phenoxyacetic acid, propanoic acid, isobutyric acid, benzoic acid, 2-methyl-benzoic acid, 2-methylbutanoic acid, 2-butenic acid, 3-phenylpropenic acid, 2,2-dimethylpropanoic acid, 2,2-dimethylbutanoic acid, 2,2-dimethylpentanoic acid, 2-ethylbutanoic acid, 3,5,5-trimethylhexanoic acid, 2-ethylhexanoic acid, neohexanoic acid, neoheptanoic acid, neodecanoic acid, octanoic acid, nonanoic acid, lauric acid, 3,5,5-trimethylpentanedioic acid, hexanedioic acid, 3,5,5-trimethylhexanedioic acid, 2,4,4-trimethylhexanedioic acid, decanedioic acid, undecanedioic acid, dodecanedioic acid, cyclohexanecarboxylic acid, 1,4-cyclohexanedicarboxylic acid, cyclohexane-1,4-diacetic acid, maleic acid, citric acid, 3-hydroxybutanoic acid, 4-hydroxybutanoic acid, 2-hydroxy-pentanoic acid, 3-hydroxypentanoic acid, 4-hydroxypentanoic acid, 5-hydroxypentanoic acid, hydroxyacetic acid, 2-hydroxyisobutyric acid, 2-hydroxypropanoic acid, 2-hydroxyhexanoic acid, hydroxypivalic acid, hydroxy-succinic acid, succinic acid, methylsuccinic acid, citraconic acid, fumaric acid, itaconic acid, oxalic acid, terephthalic acid, propenoic acid, and phthalic acid, and their corresponding methyl esters, ethyl esters, n-propyl esters, isopropyl esters, n-butyl esters, sec-butyl esters, isobutyl esters, ethylene glycol esters, and propylene glycol


esters, and the halogen substituted carboxylic acids.

Suitable carboxylic acid esters, mixed anhydrides, and pyrocarbonates are those having the exemplified substituents of the acid halogens, halogen formates, and carboxylic acid anhydrides.

- 5 Preferably, the ketone peroxide is derived from methylethyl ketone, methylisopropyl ketone, methylisobutyl ketone, acetone, cyclohexanone, and/or 2,4,4-trimethylcyclohexanone, and the acid chloride is selected from the group comprising acetyl chloride, 2-ethylhexanoyl chloride, pivaloyl chloride, neodecanoyl chloride, neoheptanoyl chloride, and isobutyryl chloride, or the
10 halogen formate is selected from the group comprising the chloroformates 2-ethylhexanoyl chloroformate, isopropyl chloroformate, sec.butyl chloroformate, ethylchloroformate, butylchloroformate, 4-tert.butyl cyclohexyl chloroformate, tetradecyl chloroformate, and hexadecyl chloroformate.


- The monoperoxy esters and monoperoxy carbonates formed in the process
15 according to the present invention may be used as starting materials for the preparation of typical mixed peroxides, mixed diperoxy esters, mixed diperoxy carbonates, and peroxy ester peroxy carbonates.

Accordingly, the present invention relates to monoperoxy ester or monoperoxy carbonate having the general formula I



wherein R_1 , R_2 , and R_3 have the identified meaning and are obtainable with the process defined hereinbefore.

The invention further relates to a process for the preparation of the mixed peroxide having the general formula IV:




wherein R_1 , R_2 , R_5 , R_6 , and R_7 are independently selected from the group


comprising hydrogen, C₁-C₂₀ alkyl, C₃-C₂₀ cycloalkyl, C₆-C₂₀ aryl, C₇-C₂₀ aralkyl, and C₇-C₂₀ alkaryl, or R₁ and R₂ may form a C₃-C₁₂ cycloalkyl group, which groups may include linear or branched alkyl moieties, and each of R₁, R₂, R₅, R₆, and R₇ may optionally be substituted with one or more groups selected from hydroxy, alkoxy, linear or branched alkyl, aryloxy, halogen, ester, carboxy, nitrile, and amido,

R₃ and R₄ are independently selected from the group comprising C₁-C₂₀ alkyl, C₃-C₂₀ cycloalkyl, C₆-C₂₀ aryl, C₇-C₂₀ aralkyl, and C₇-C₂₀ alkaryl, which groups may include linear or branched alkyl moieties, and each of R₃ and R₄ may optionally be substituted with one or more groups selected from hydroxy, alkoxy, linear or branched alkyl, aryloxy, halogen, ester, carboxy, nitrile, and amido,

wherein a monoperoxy ester or monoperoxy carbonate and any pair of the optionally substituted R₄, R₅, R₆, and R₇ may form a ring, which process comprises the reaction of the corresponding monoperoxy ester or monoperoxy carbonate with the general formula I:



wherein R₁, R₂, and R₃ have the identified meaning, with an alkyl vinyl ether with the general formula Va, or an acetal with the general formula Vb:




wherein R₄, R₅, R₆, and R₇ have the identified meaning, in the presence of an acid catalyst.

R₅, R₆, and R₇ preferably are hydrogen.

The monoperoxy ester or monoperoxy carbonate used in this process preferably is obtained in the above preparation process for these monoperoxy ester and monoperoxy carbonates.

The monoperoxy ester or monoperoxy carbonate is reacted with an alkyl vinyl ether or acetal with the general formula Va or Vb:



wherein the groups R_4 , R_5 , R_6 , and R_7 have the meaning as specified above. R_5 , R_6 , and R_7 preferably are hydrogen.

Specific examples of the alkyl vinyl ether with the general formula Va are: vinyl 2,2-bis(vinyloxymethyl)butyl ether, 2-methoxy-2-butene, n-propyl vinyl ether, 1-ethoxy-4-methyl-1-nonene, tert.amyl vinyl ether, 2,2-bis (4-vinyloxyphenyl)propane, hexadecyl vinyl ether, methyl vinyl ether, 4-methylhexyl vinyl ether, 2-(2-ethoxyethoxy)ethyl vinyl ether, 2-methoxyethyl vinyl ether, 2-vinyloxy ethanol, 4-methyl-1-decenyl vinyl ether, benzyl 1-methyl vinyl ether, butanediol divinyl ether, tert.butyl vinyl ether, isobutyl vinyl ether, cyclohexanedimethanol divinyl ether, cyclohexyl vinyl ether, ethyleneglycol divinyl ether, 1-ethoxy-4-(1-ethoxyvinyl)-3,3,5,5-tetramethylcyclohexene, isopropyl vinyl ether, ethyl vinyl ether, tetraethyleneglycol divinyl ether, 1,1,3-trimethoxypropene, 1-methoxy-1-buten-3-yne, heptyl vinyl ether, 4-(1-ethoxyvinyl)-3,3,5,5-tetramethylcyclohexanone, 2-butoxyethyl vinyl ether, divinyl ether, 1,3-divinyloxy-2,2-dimethylpropane, 4-vinyloxybutanol, diethyleneglycol divinyl ether, 4-(vinyloxymethyl) cyclohexylmethanol, isopentyl vinyl ether, diethyleneglycol monovinyl ether, n-butyl vinyl ether, 1,4-bis(2-vinyloxyethyl)benzene, hexanediol divinyl ether, 1-methoxy-1,3-butadiene, decyl vinyl ether, 4-(allyloxymethyl)-1,3-dioxolan-2-one, 1,1-diethylpropyl vinyl ether, 2-methoxyvinyl benzene, octyl vinyl ether, bis(vinyloxy)methane, 1,4-dimethoxy-1,3-butadiene, 2,3-dimethoxy-1,3-butadiene, triethyleneglycol divinyl ether, pentyl vinyl ether, octadecyl vinyl ether, 2-methoxypropene, triethyleneglycol methyl vinyl ether, 2,3-epoxypropyl vinyl ether, dodecyl vinyl ether, 1,1-bis(vinyloxy) butane, hexyl vinyl ether, 6-vinyloxyhexanol, (z)-1-methoxy-1-buten-3-yne, phenyl vinyl ether, 2-ethylhexyl vinyl ether, poly-THF-divinyl ether, pluriol-E-200-divinyl ether, trimethylolpropane trivinyl ether,

aminopropyl vinyl ether, 2-diethylaminoethyl vinyl ether, 2-ethoxy propene, 2-isobutoxypropene, 2-ethoxy-2-butene, 2-isobutoxy-2-propene, and ethyl propenyl ether. It is noted that if a divinyl ether is used, that products will be formed that have two moieties of formula IV that are linked through the mutual R₄ group.


Examples of trisubstituted and cyclic alkyl vinyl ethers are 1-methoxy-2-methyl cyclohexene and 2-methoxy-2-methyl-2-butene. Examples of the cyclic alkyl vinyl ethers are 2-methyl-2,3-dihydrofuran, 2,3-dihydrofuran, 2-methyl-3,4-dihydropyran, 3,4-dihydropyran, and 1-methoxy cyclohexene.

- 10 Examples of acetals according to general formula Vb are 2,2-dimethoxypropane, 2,2-diethoxypropane, 1,1-dimethoxybutane, 2-propyl-1,3-dioxolane, 1,1-dimethoxyethane, 1,1-diethoxyethane, 1,1-diethoxypropane, and 1,1-dimethoxycyclohexane.

The alkyl vinyl ether or acetal addition reaction is carried out under conditions conventional for this type of addition reaction. The temperature generally is in the range of 0-50°C and preferably is between 10-25°C. The reaction is carried out in the presence of an acid catalyst. The amount of acid catalyst generally is 0.01-30 g/mole and preferably 0.1-15 g/mol of monoperoxy ester or monoperoxy carbonate.


- 20 The acid catalyst for the process is a conventional acidic catalyst such as a C₁-C₁₀ alkane or aryl sulphonic acid, a halogenated C₁-C₁₀ alkane sulphonic acid or a mixture of one or more of these compounds. The preferred catalysts for use are, but are not limited to, p-toluenesulfonic acid and methane sulfonic acid.

- 25 The invention further relates to these mixed peroxides as such having the general formula IV:




wherein R₁, R₂, R₃, R₄, R₅, R₆, and R₇ have the identified meaning. These mixed peroxides are obtainable with the above alkyl vinyl ether addition reaction.


The present invention further relates to a process for the preparation of a mixed diperoxy ester and a peroxy ester peroxy carbonate having the general formula VI:



- 5 wherein R_1 and R_2 are independently selected from the group comprising hydrogen, C_1 - C_{20} alkyl, C_3 - C_{20} cycloalkyl, C_6 - C_{20} aryl, C_7 - C_{20} aralkyl, and C_7 - C_{20} alkaryl, or R_1 and R_2 form a cycloalkyl group, which groups may include linear or branched alkyl moieties, and each of R_1 and R_2 may optionally be substituted with one or more groups selected from hydroxy, alkoxy, linear or branched
 10 alkyl, aryloxy, halogen, ester, carboxy, nitrile, and amido, and R_3 and R_8 are mutually different and independently selected from the group comprising C_1 - C_{20} alkyl, C_3 - C_{20} cycloalkyl, C_6 - C_{20} aryl, C_7 - C_{20} aralkyl, and C_7 - C_{20} alkaryl, which groups may include linear or branched alkyl moieties, and each of R_3 and R_8 may optionally be substituted with one or more groups selected from hydroxy,
 15 alkoxy, linear or branched alkyl, aryloxy, halogen, ester, carboxy, nitrile, and amido, in which process a monoperoxy ester or monoperoxy carbonate with the general formula I:




- 20 wherein R_1 , R_2 , and R_3 have the identified meaning is reacted with a carboxylic acid anhydride with the general formula VII:



wherein R_8 has the identified meaning, in the presence of catalyst.

In the preparation process of these mixed diperoxy esters and peroxy ester peroxy carbonates the carboxylic acid anhydride has the general formula VII:



wherein R₈ has the identified meaning.

Suitable carboxylic acid anhydrides are those derived from the following carboxylic acids: acetic acid, phenylacetic acid, phenoxyacetic acid, propanoic acid, isobutyric acid, benzoic acid, 2-methyl-benzoic acid, 2-methylbutanoic acid, 2-butenoic acid, 3-phenylpropenic acid, 2,2-dimethylpropanoic acid, 2,2-dimethylbutanoic acid, 2,2-dimethylpentanoic acid, 2-ethylbutanoic acid, 3,5,5-trimethylhexanoic acid, 2-ethylhexanoic acid, neohexanoic acid, neoheptanoic acid, neodecanoic acid, octanoic acid, nonanoic acid, lauric acid, 3,5,5-trimethylpentanedioic acid, hexanedioic acid, 3,5,5-trimethylhexanedioic acid, 2,4,4-trimethylhexanedioic acid, decanedioic acid, undecanedioic acid, dodecanedioic acid, cyclohexanecarboxylic acid, 1,4-cyclohexanedicarboxylic acid, cyclohexane-1,4-diacetic acid, maleic acid, citric acid, 3-hydroxybutanoic acid, 4-hydroxybutanoic acid, 2-hydroxy-pentanoic acid, 3-hydroxypentanoic acid, 4-hydroxypentanoic acid, 5-hydroxypentanoic acid, hydroxyacetic acid, 2-hydroxyisobutyric acid, 2-hydroxypropanoic acid, 2-hydroxyhexanoic acid, hydroxypivalic acid, hydroxy-succinic acid, succinic acid, methylsuccinic acid, citraconic acid, fumaric acid, itaconic acid, oxalic acid, terephthalic acid, propenoic acid, and phthalic acid, and their corresponding methyl esters, ethyl esters, n-propyl esters, isopropyl esters, n-butyl esters, sec-butyl esters, isobutyl esters, ethylene glycol esters, and propylene glycol esters, and the halogen substituted carboxylic acids.

The reaction of the monoperoxy ester or monoperoxy carbonate with the carboxylic acid anhydride is carried out under conditions conventional for this type of reaction.


The temperature is in the range of 0-50°C, preferably between 10-25°C. The reaction is carried out in the presence a catalyst.

The amount of catalyst generally is 0.01-30 g/mole and preferably 0.1-15 g/mol of the monoperoxy ester or monoperoxy carbonate. The catalyst may be a basic catalyst or an acid catalyst.

The acid catalyst for the process is a conventional acidic catalyst such as a C₁-C₁₀ alkane or aryl sulphonic acid, a halogenated C₁-C₁₀ alkane sulphonic acid or a mixture of one or more of these compounds. The preferred catalysts for use are, but are not limited to, p-toluenesulfonic acid and methane sulfonic acid.

Examples of a suitable basic catalyst are sodium acetate, potassium acetate, sodium carbonate, potassium carbonate, sodium hydroxide, and potassium hydroxide.


In addition, the present invention includes the following mixed diperoxy esters and peroxy ester peroxy carbonates having the general formula VI:



wherein R₁, R₂, R₃, and R₈ have the identified meaning.

These mixed diperoxy esters and peroxy ester peroxy carbonates are obtainable with the above preparation process using a carboxylic acid anhydride as a reactant.


The present invention further relates to a process for the preparation of a mixed diperoxy carbonate having the general formula VIII:




wherein R₁ and R₂ are independently selected from the group comprising hydrogen, C₁-C₂₀ alkyl, C₃-C₂₀ cycloalkyl, C₆-C₂₀ aryl, C₇-C₂₀ aralkyl, and C₇-C₂₀ alkaryl, or R₁ and R₂ form a C₃-C₁₂ cycloalkyl group, which groups may include linear or branched alkyl moieties, and each of R₁ and R₂ may optionally be substituted with one or more groups selected from hydroxy, alkoxy, linear or branched alkyl, aryloxy, halogen, ester, carboxy, nitrile, and amido, and R₃ and R₉ are independently selected from the group comprising C₁-C₂₀ alkyl,

C₃-C₂₀ cycloalkyl, C₆-C₂₀ aryl, C₇-C₂₀ aralkyl, and C₇-C₂₀ alkaryl, which groups may include linear or branched alkyl moieties, and R₃ and R₉ may optionally be substituted with one or more groups selected from hydroxy, alkoxy, linear or branched alkyl, aryloxy, halogen, ester, carboxy, nitrile, and amido,

- 5 which process comprises the reaction of the monoperoxy carbonate with the general formula I':



wherein R₁ and R₂ have the identified meaning, with halogen formate with the general formula III':



10

wherein R₉ has the identified meaning, with the proviso that R₉ is not identical with R₃.

15


The monoperoxy carbonate used is obtainable by the above-described preparation process. Suitable halogen formates are those generally and specifically described in relation to this preparation process for monoperoxy carbonate. Preferably, the reaction is carried out in a suitable solvent.

20

Generally, the process is as claimed in claim 13, where the equivalent amount of acid halogen or halogen formate is in the range of 1-5 equivalents, preferably 3.0-5.0 equivalents. These numbers of equivalents are selected such that the chemical yield is optimal.

In general, the same reaction conditions may be used as for the monoperoxy carbonates preparation process.

Finally, the invention relates to mixed diperoxy carbonate having the general formula VIII:



wherein R_1 , R_2 , R_3 and R_9 have the identified meaning, which is obtainable with the above preparation process.

The peroxides according to the present invention and produced with the preparation processes according to the present invention may be used as initiators for polymer production and in particular for the preparation of poly(vinylchloride), acrylic (co)polymers, polystyrene, polyethylene, for curing unsaturated polyester resins, and for polymer modification (such as grafting of monomers).

In the present invention, the polymerization is conducted by any conventional process, except that a specified radical polymerization initiator (or composition) is used. The polymerization processes may be carried out in the usual manner, for example in bulk, suspension, emulsion or solution. In the case of the production of ethylene (co)polymers, the reaction is usually carried out under high pressure, e.g. about 1000 to about 3500 bar.

The amount of initiator, which varies depending on the polymerization temperature, the capacity for removing the heat of polymerization, and, where applicable, the kind of monomer to be used and the applied pressure, should be an effective amount for achieving polymerization. Usually, from 0.001-25% by wt of peroxide, based on the weight of the (co)polymer, is employed. Preferably, from 0.001-20% by wt of peroxide is employed and most preferably from 0.001-15% by wt.

For most reactions within the present invention the polymerization temperature usually is 30° to 350°C, preferably 40° to 300°C. In general, if the temperature is below 30°C, the polymerization time becomes too long. However, when it exceeds 350°C, the radical polymerization initiator is spent in the initial stage of the polymerization, making it difficult to attain a high conversion. In order to reduce the amount of unreacted monomer, however, it is also possible to conduct polymerization using a temperature profile, e.g., to perform the initial

polymerization at below 100°C and then elevate the temperature above 100°C to complete the polymerization. These variations are all known to the man skilled in the art, who will have no difficulty selecting the reaction conditions of choice, depending on the particular polymerization process and the specific radical polymerization initiator to be used.

- Suitable monomers for polymerization using the ketone peroxides according to the present invention are olefinic or ethylenically unsaturated monomers, for example substituted or unsubstituted vinyl aromatic monomers, including styrene, alpha-methylstyrene, p-methylstyrene, and halogenated styrenes; divinylbenzene; ethylene; ethylenically unsaturated carboxylic acids and derivatives thereof, such as (meth)acrylic acids, (meth)acrylic esters, butylacrylate, hydroxyethyl (meth)acrylate, methylmethacrylate, 2-ethylhexyl acrylate, 2-ethylhexyl methacrylate, and glycidyl methacrylate; ethylenically unsaturated nitriles and amides, such as acrylonitrile, methacrylonitrile, and acrylamide; substituted or unsubstituted ethylenically unsaturated monomers, such as butadiene, isoprene, and chloroprene; vinyl esters, such as vinyl acetate and vinyl propionate; ethylenically unsaturated dicarboxylic acids and their derivatives including mono- and diesters, anhydrides and imides, such as maleic anhydride, citraconic anhydride, citraconic acid, itaconic acid, nadic anhydride, maleic acid, fumaric acid, aryl, alkyl and aralkyl citraconimides and maleimides; vinyl halides, such as vinyl chloride and vinylidene chloride; vinyl ethers, such as methylvinyl ether and n-butylvinyl ether; olefins, such as isobutene and 4-methylpentene; allyl compounds, such as (di)allyl esters, for example diallyl phthalates, (di)allyl carbonates, and triallyl (iso)cyanurate.
- During (co)polymerization, the formulations may also contain the usual additives and fillers. As examples of such additives may be mentioned: stabilizers such as inhibitors of oxidative, thermal or ultraviolet degradation, lubricants, extender oils, pH controlling substances, such as calcium carbonate, release agents, colourants, reinforcing or non-reinforcing fillers such as silica, clay, chalk, carbon black, and fibrous materials, such as glass fibres, plasticizers, diluents, chain transfer agents, accelerators, and other types of

peroxides. These additives may be employed in the usual amounts.

Finally, the polymerization process of the present invention can be employed to introduce functional groups into the (co)polymers. This may be accomplished by employing a peroxide which contains one or more functional groups attached thereto. These functional groups remain intact in the free radicals
5 formed by the ketone peroxides and thus are introduced into the (co)polymer. Conventional polymerization conditions and equipment may be used to achieve this object of the present invention.

The peroxides according to the invention which may be used as a curing
10 agents for the unsaturated polyesters and unsaturated polyester resins according to the present invention usually include an unsaturated polyester and one or more ethylenically unsaturated monomers. Suitable polymerizable monomers include styrene, alpha-methylstyrene, p-methylstyrene, chlorostyrenes, bromostyrenes, vinylbenzyl chloride, divinylbenzene, diallyl
15 maleate, dibutyl fumarate, triallyl phosphate, triallyl cyanurate, diallylphthalate, diallyl fumarate, methyl (meth)acrylate, n-butyl (meth)acrylate, ethyl acrylate, and mixtures thereof which are copolymerizable with the unsaturated polyesters. The unsaturated polyesters are, for example, polyesters as they are obtained by esterifying at least one ethylenically unsaturated di- or
20 polycarboxylic acid, anhydride or acid halide, such as maleic acid, fumaric acid, glutaconic acid, itaconic acid, mesaconic acid, citraconic acid, allylmalonic acid, tetrahydrophthalic acid, and others, with saturated and unsaturated di- or polyols, such as ethylene glycol, diethylene glycol, triethylene glycol, 1,2- and 1,3-propanediols, 1,2-, 1,3-, and 1,4-butanediols, 2,2-dimethyl-1,3-
25 propanediols, 2-hydroxymethyl-2-methyl-1,3-propanediol, 2-buten-1,4-diol, 2-butyne-1,4-diol, 2,4,4-trimethyl-1,3-pentanediol, glycerol, pentaerythritol, mannitol, and others. The di- or polycarboxylic acids may be partially replaced by saturated di- or polycarboxylic acids, such as adipic acid, succinic acid, and others, and/or by aromatic di- or polycarboxylic acids, such as phthalic acid, trimellitic acid, pyromellitic acid, isophthalic acid, and terephthalic acid. The
30 acids used may be substituted with groups such as halogen. Suitable

halogenated acids include, for example, tetrachlorophthalic acid and tetrabromophthalic acid.

The peroxides of the present invention are suited for use in the modification of polymers such as degradation, crosslinking or grafting. More particularly, these
5 peroxides can be employed in processes for grafting monomers onto polymers such as polyolefins and elastomers, and for the functionalization of polyolefins in the case of functional group-containing ketone peroxides of the present invention.

In general, the peroxide may be brought into contact with the (co)polymer in
10 various ways, depending upon the particular object of the modification process. The polymer material may be in the solid state, molten state, in the form of a solution in the case of an elastomer, in a plastic state or in any physical form including finely divided particles (flake), pellets, film, sheet, in the melt, in solution, and the like. Polymers may also be in the liquid form, e.g. liquid
15 rubbers.


In general, any (co)polymer comprising abstractable hydrogen atoms, in particular polyolefins, can be modified by the present process.

The amount of peroxide used in the modification process of the present invention should be an effective amount for achieving significant modification of
20 the (co)polymer when treating a (co)polymer. More particularly, from 0.001-15.0 weight percent of peroxide, based on the weight of the (co)polymer, should be employed. More preferably, from 0.005-10.0% by wt percent is employed. Most preferably, an amount of 0.01-5.0% by wt is employed.

The peroxide may also be used for the modification of a chemical, whereby said
25 chemical is reacted with the radicals formed upon decomposition of the peroxide, or with non-radical decomposition products that are formed when the peroxide is decomposed. As indicated above for the modification of polymers, the modification of chemicals will often, but not necessarily, involve the abstraction of protons from said chemical. An example of a modification
30 reaction is the epoxidation of olefinically unsaturated compounds.

It is noted that in the preparation processes the ketone peroxide may be pure

(T3) peroxide (as shown in the general formula II) or may comprise 5%-30%, such as 5%-25% and 10%-15%, of the (T3) derived peroxide, (T4), having the general formula II':



5 wherein R₁ and R₂ have the identified meaning. The presence of the corresponding T4 peroxide has no effect the on peroxide's use as polymerization initiator, curing agent, and modifying agent.

The peroxides can be prepared, transported, stored, and applied in the form of powders, granules, pellets, pastilles, flakes, slabs, pastes, solid masterbatches,
10 and liquids. These formulations may have the form of a dispersion, such as a suspension or an emulsion. They can be be phlegmatized if necessary, depending on the particular peroxide and its concentration in the formulation.

Which of these forms is to be preferred depends partly on the application for which it will be used and partly on the manner in which it will be mixed. Also,
15 considerations of safety may play a role to the extent that phlegmatizers may have to be incorporated into certain compositions to ensure their safe handling.

The formulations of the present invention are transportable, storage stable, and contain 1.0-90% by wt of one or more peroxides according to the present invention. Transportable means that the formulations of the present invention
20 have passed the pressure vessel test (PVT). Storage stable means that the formulations of the present invention are both chemically and physically stable during a reasonable storage period under standard conditions.

More preferred formulations in accordance with the present invention contain 10-70% by wt of one or more of the ketone peroxides, most preferably these
25 formulations contain 20-60% by wt of the ketone peroxides.

The formulations of the present invention can be liquids, solids or pastes depending on the melting point of the peroxide and the dilu nt employed. Liquid

formulations can be made using liquid phlegmatizers for the ketone peroxide, liquid plasticizers, organic peroxides, and mixtures thereof as the diluent. The liquid component is generally present in an amount of 1-99% by wt of the composition, preferably 10-90% by wt, more preferably 30-90% by wt, and most preferably 40-80% by wt of the liquid formulation consists of liquid diluents.

It should be noted that certain phlegmatizers may not be suitable for use with all of the ketone peroxides of the present invention. More particularly, in order to obtain a safe composition, the phlegmatizer should have a certain minimum flash point and a boiling point relative to the decomposition temperature of the ketone peroxide such that the phlegmatizer cannot be boiled off leaving a concentrated, unsafe ketone peroxide composition behind. Thus, the lower-boiling phlegmatizers mentioned below may only be useful, for example, with particular substituted ketone peroxides of the present invention which have a low decomposition temperature.

In liquid formulations a liquid carrier or diluent is used. Preferably, this carrier or diluent is a solvent. For the monoperoxy esters and monoperoxy carbonates according to the present invention both polar and apolar solvents may be used. For the diperoxy esters, diperoxy carbonates, and mixed diperoxides only apolar solvents are used. Examples of the solvents are those given for the preparation of the various ketone peroxides.

In the solid and/or paste formulations of the present invention solid carrier materials are employed. Examples of such solid carriers are low-melting solids, such as dicyclohexylphthalate, dimethyl fumarate, dimethylisophthalate, triphenylphosphate, glyceryltribenzoate, trimethylolethane tribenzoate, dicyclohexylterephthalate, paraffinic waxes, dicyclohexylisophthalate, polymers, and inorganic supports. Inorganic supports include materials such as fumed silica, precipitated silica, hydrophobic silica, chalk, whiting, surface-treated clays such as silane-treated clays, calcined clays, and talc.

Polymers useful in the formulations of the present invention include polyethylene, polypropylene, ethylene/propylene copolymers, ethylene/propylene/diene monomer terpolymers, chlorosulphonated

polyethylene, chlorinated polyethylene, polybutylene, polyisobutylene, ethylene/vinyl acetate copolymers, polyisoprene, polybutadiene, butadiene/styrene copolymers, natural rubber, polyacrylate rubber, butadiene/acrylonitrile copolymers, acrylonitrile/butadiene/styrene terpolymers, 5 silicone rubber, polyurethanes, polysulphides, solid paraffins, and polycaprolactone.

Storage stable formulations must be both physically and chemically stable. By physically stable formulations are meant those formulations which do not suffer from significant phase separation upon storage. The physical stability of the 10 present formulations can, in some instances, be improved by the addition of one or more thixotropic agents selected from cellulose esters, hydrogenated castor oil, and fumed silica. Examples of such cellulose esters are the reaction products of cellulose and acid compounds selected from, for example, acetic acid, propionic acid, butyric acid, phthalic acid, trimellitic acid, and mixtures 15 thereof.

By chemically stable formulations are meant those formulations which do not lose a significant amount of their active oxygen content upon storage. The chemical stability of the present formulations can, in some instances, be improved by the addition of one or more known additives including 20 sequestering agents such as dipicolinic acid and/or antioxidants such as 2,6-di(t-butyl)-4-methyl phenol and para-nonyl phenol.

The formulations of the present invention may also contain optional other additives as long as these do not have a significant adverse effect on the transportability and/or storage stability of the formulations. As examples of such 25 additives may be mentioned: anti-caking agents, free-flowing agents, anti-ozonants, anti-oxidants, anti-degradants, U.V. stabilizers, coagents, fungicides, antistats, pigments, dyes, coupling agents, dispersing aids, blowing agents, lubricants, process oils, and mould-release agents. These additives may be employed in their usual amounts.

30 The ketone peroxides according to the invention may also be used as a dispersion, preferably in a polar medium. The medium in which the initiator

according to the invention is dispersed should be inert towards the initiator and so polar that the initiator will hardly dissolve in it. The initiator preferably is dispersed in water or an alcohol. Most preferable is a dispersion in water. The use of such a medium makes for comparatively easy removal of any remnant,
5 for example after the modification of the (co)polymer if so desired. Furthermore, the use of water or alcohols is attended with far fewer organoleptic and other drawbacks than the use of organic diluents, such as toluene and xylene, which has been common up to now.

As is well-known to the skilled person, the use of other adjuvants in initiator
10 dispersions may be advisable or even essential in order to ensure the dispersion's chemical and/or physical stability for a sufficiently long period of time. For instance, if the storage temperature of the initiator dispersion is lower than the freezing point of the medium in which the initiator is dispersed, an appropriate freezing point depression agent can be added to counteract
15 freezing. Also, a wide range of substances can be used for altering the rheology of the formulation. To this end generally use is made of one or more surface-active materials and one or more thickeners. If so desired, other additives may be incorporated into the formulation. As examples of such additives may be mentioned pH buffers, biocides, chemical stabilizers which
20 counteract premature decomposition of the initiator, and anti-agers which counteract particle size growth in the dispersion.

Using mixtures of monoperoxy esters or monoperoxy carbonates with other peroxides, for example diperoxy esters or diperoxy carbonates, a wide range of reactivities can be achieved. The half-life time of the mixture of the different
25 peroxides normally lies between the half-life of each of the pure peroxides. This is useful for example in ethylene polymerization, where the optimum efficiency of the peroxide (mixture) in the polymerization process is very dependent on the reactivity of the peroxide (mixture).

The following examples illustrate the preparation processes for the monoperoxy
30 ester, mixed diperoxy carbonate, monoperoxy carbonate, mixed diperoxy esters, peroxy ester peroxy carbonates, and mixed peroxides according to the

present invention and their application.

Example 1. Preparation of 1-(2-ethylhexanoylperoxy)-1,3-dimethylbutylperoxy-1,3-dimethylbutyl hydroperoxide.

5 In to a 250 ml beaker were charged 75 g of methylisobutylketone peroxide in isododecane (containing 0.0007 mole T4 and 0.0970 mole T3) and 20 g of NaCl-25%. The pH was adjusted to 13.5 with KOH-45% at a temperature of 8-12°C.

Next 16.3 g of 2-ethylhexanoylchloride (0.10 mole; 1 eq) were dosed in 15 min. simultaneously with lye, keeping the pH at >13.5. The mixture was stirred for 10 another 90 min. at 3-5°C.

After separation of the water layer the organic layer was washed with NaOH-4N and NaHCO₃-6%. The product was dried over magnesium sulphate.

Yield 80.5 g of product with an active oxygen content of 5.78%. (chemical 15 yield:99%).

Ratio mono:bis = 92:8.

Example 2. As example 1, but with a ratio of 2.1 moles of 2-ethylhexanoyl chloride to 1 mole of methylisobutylketone peroxide in isododecane. Here the 20 product also was the monoperoxy ester. Ratio mono:bis = 88:12.

Example 3. Preparation of 1-(1-(2-ethylhexanoylperoxy)-1-methylpropylperoxy)-1-methylpropyl hydroperoxide. As in example 1, but using methylethylketone peroxide instead of methylisobutylketone peroxide. 25 Chemical yield 89%. Ratio mono:bis = 70:30

Example 4. Preparation of 1-(1-(2-methylpropanoylperoxy)-1,3-dimethylbutylperoxy)-1,3-dimethylbutyl hydroperoxide.

In to a 250 ml beaker were charged 25 g of methylisobutylketone peroxide in 30 isododecane (containing 0.0005 mole T4 and 0.0340 mole T3) and 7 g of NaCl-25%. The pH was adjusted to 13.5 with KOH-45% at a temperature of 8-12°C.

25

Next 3.7 g of isobutyrylchloride (0.0347 mole; 1 eq) were dosed in 15 min. simultaneously with the lye, keeping the pH at >13.5. The mixture was stirred for another 90 min. at 3-5°C.

After separation of the water layer the organic layer was washed with water and

5 NaHCO_3 -6%. The product was dried over magnesium sulphate.

Yield 24.5 g of product with an active oxygen content of 6.10%. (chemical yield:90%).

Ratio mono:bis = 88:12.

10 **Example 4A.** Preparation of 1-Hydroperoxy-1,2-dimethylpropyl 1-(2-methylpropanoylperoxy)-1,2-dimethylpropyl peroxide.

As example 4, but by using 50 g methylisopropylketone peroxide in isododecane.

Yield 49.1 g with AO 5,69% (Chemical Yield 78%).

15

Example 5. Preparation of 1-(1-(2,2-dimethylpropanoylperoxy)-1,3-dimethylbutylperoxy)-1,3-dimethylbutyl hydroperoxide.

Into a 250 ml beaker were charged 25 g of methylisobutylketone peroxide in isododecane (containing 0.0005 mole T4 and 0.0340 mole T3) and 7 g of NaCl-25%. The pH was adjusted to 13.5 with KOH-45% at a temperature of 8-12°C.

20

Next 4.2 g of pivaloyl chloride (0.0347 mole; 1 eq) were dosed in 15 min. simultaneously with the lye, keeping the pH at >13.5. The mixture was stirred for another 90 min. at 3-5°C.

After separation of the water layer the organic layer was washed with water and

25 NaHCO_3 -6%. The product was dried over magnesium sulphate.

Yield 24.5 g of product with an active oxygen content of 6.10%. (chemical yield:90%).

Ratio mono:bis = 97:3.

30 **Example 6.** As example 5 but with a ratio of 2.1 moles of pivaloyl chloride to 1 mole of methylisobutylketone peroxide in isododecane. Here the major product

also was the monoperoxyester. Ratio mono:bis = 65:35.

Example 7. Preparation of 1-(1-(2,2-dimethylpropanoylperoxy)-1-methylpropylperoxy)-1-methylpropyl hydroperoxide.

- 5 As example 6, but with a ratio of 2.1 moles of pivaloyl chloride to 1 mole of methylethylketone peroxide in isododecane. Here the major product also was the monoperoxy ester. Ratio mono:bis = 60:40.

Example 8. Preparation of 1-(1-isopropoxycarbonylperoxy)-1,3-dimethylbutylperoxy-1,3-dimethylbutyl hydroperoxide.

- 10 Into a 250 ml beaker were charged 30 g of methylisobutylketone peroxide in isododecane (containing 0.0003 mole T4 and 0.0404 mole T3) and 70 ml pentane. To this mixture 6.5 g pyridine were added at a temperature of 8-12°C. Next 10 g of isopropyl chloroformate (0.0814 mole; 2.0 eq) were dosed in 10 min. at a temperature of 6-8°C. The mixture was stirred for another 60 min. at 4-6°C.

The reaction mixture was poured into an ice/water mixture and the organic layer was separated and washed twice with H₂SO₄-2N, once with NaOH-4N, and once with water.

- 20 The product was dried over magnesium sulphate and the pentane was evaporated.

Yield 28.6 g of product with an active content oxygen of 5.83%. (chemical yield:90%).

Ratio mono:bis = 50:50.

25

Example 9. Preparation of 1-acetylperoxy-1,3-dimethylbutyl-1-(2-ethylhexanoylperoxy) 1,3-dimethylbutyl peroxide.

- 30 Into a 50 ml beaker were charged 10 g of 1-(2-ethylhexanoylperoxy)-1,3-dimethylbutylperoxy-1,3-dimethylbutyl hydroperoxide (0.00973 mole) and 2 g of acetic anhydride (0.0195 mole) at a temperature of 15°C. To this mixture 0.5 g potassium carbonate acid was added slowly, keeping the temperature at 15-

20°C. The mixture was stirred for another 60 min. at 20°C, washed twice with water, once with NaHCO₃-6% and dried over magnesium sulphate.

Yield 10 g of product with an active oxygen content of 3.20% (chemical yield:66%).

5 **Example 9A.** Preparation of 1-Acetylperoxy-1,3-dimethylbutyl-1-(2-methylpropanoylperoxy)-1,3-dimethyl peroxide.

As example 9, but by using 25 g of 1-(1-(2-Methylpropanoylperoxy)-1,3-dimethylbutylperoxy-1,3-dimethylbutyl hydroperoxide from example 4.

Yield 25.9 g with AO 7.90% (Chemical Yield 96%).

10

Example 9B. Preparation of 1-Acetylperoxy-1,2-dimethylpropyl 1-(2-methylpropanoylperoxy)-1,2-dimethylpropyl peroxide.

As example 9, but by using 30 g of 1-Hydroperoxy-1,2-dimethylpropyl 1-(2-methylpropanoylperoxy)-1,2-dimethylpropyl peroxide from example 4A.

15 Yield 25.4 g with AO 5.26% (Chemical Yield 80%).

Example 10. Preparation of 1-(2-ethylhexanoylperoxy)-1,3-dimethylbutyl-1-(1-isobutoxyethyl)peroxy 1,3-dimethylbutyl peroxide.

20 Into a 50 ml beaker were charged 20 g of 1-(2-ethylhexanoylperoxy)-1,3-dimethylbutylperoxy-1,3-dimethylbutyl hydroperoxide (0.0241 mole) and 0.2 g of p-toluenesulphonic acid monohydrate at a temperature of 20°C. Then 2.42 g of isobutylvinylether were dosed in 2 min. , keeping the temperature at 10°C by cooling with an icewater bath. The mixture was stirred for another 10 min. at 20°C, washed with NaHCO₃-6% and dried over magnesium sulphate.

25 Yield 20.6 g of product with an active oxygen content of 4.19% (chemical yield:75%).

Example 11. Preparation of 1-(2,2-dimethylpropanoylperoxy)-1,3-dimethylbutyl, 1-((1-isobutoxyethyl)peroxy)-1,3-dimethylbutyl peroxide.

30 As example 10, but starting from the product obtained in example 5.

Chemical yield 80%.

Example 12. As example 10, with the same result a mixture of 1-(2-ethylhexanoylperoxy)-1,3-dimethylbutylperoxy-1,3-dimethylbutyl hydroperoxide containing 10-25% 1-hydroperoxy-1,3-dimethylbutyl peroxy-2-ethylhexanoate was converted to the mixed peroxide.

Example 13. Preparation of 1-(1-(1 isobutoxyethylperoxy)-1-methylpropyl peroxy 1-methylpropylperoxy-2-ethylhexanoate. As in example 10, but using the hydroperoxide prepared in example 3 as starting material.

Example 14. Preparation of 1-(1-acetylperoxy-1,3-dimethylbutylperoxy)-1,3-dimethylbutyl hydroperoxide. Into a 250 ml. beaker were charged 75 g of methylisobutylketone peroxide in isododecane (containing 0.0007 mole T4 with KOH-45% and 0.0970 mole T3) and 20 g of NaCl-25%. The pH was adjusted to 13.5 with KOH-45% at a temperature of 8-12°C.

The 7.9 g of acetyl chloride (0.10 mole) was dosed in 15 min. simultaneously with the lye, keeping the pH at >13.5. The mixture was stirred for another 90 min. at 3-5°C. After separation of the water layer the organic layer was washed with NaOH-4N and NaHCO₃-6%. The product was dried over magnesium sulphate. Yield 68.5 g of product with an active oxygen content of 6.4%. (chemical yield: 90%). This peroxide has a half life time of 1 h at 96°C (determined with DSC). By mixing this product with its bis-adduct (having a t_{1/2} of 1 h at 84°C) in a certain ratio, a half-life time of 1 h can be achieved between 84 and 96°C. For example a 50%:50% (mole/mole) mixture gives a half-life time of 1h at 92°C.

Example 15. Polymerization of vinyl chloride.

Peroxyesters of the present invention with 1-hour half-life temperatures in the range of 40°-60°C were evaluated with good results in vinyl chloride polymerization. The polyvinyl chloride was produced according to an experimental procedure to be used for the 5 liter autoclave, the conversion in

time being measured via the "butane tracer technique" (ref.: T.Y. Xie, A.E. Hamielek, P.E. Wood, O.R. Woods and H. Westmijze, J. Appl. Pol. Sci., Vol. 41 (1990)). A 5-liter stainless steel reaction vessel provided with: 1 baffle, a three-bladed stirrer, ($n=450\text{rpm}$), a pressure transducer, a nitrogen purge, and the sampling device for the butane tracer technique, was charged with 2700 g demineralized water and 0,15% Gohsenol KP-08 (1.0125g) on vinyl chloride, and with a buffer: 1g Na_2HPO_4 ex Baker, no. 0303 + 1g Na_2HPO_4 ex Baker no. 0306. The vessel was closed and pressurized with 15 bar nitrogen. The vessel was evacuated and pressurized with nitrogen (5 bar) at least three times.

Subsequently, the vessel was fed the peroxy ester of the present invention identified in Table 1 as an initiator. The vessel was evacuated again and subsequently charged with vinyl chloride. The temperature was increased from ambient to the polymerization temperature (37-62°C) in about 30 minutes (37 and 42°C) and up to 60 minutes for the higher temperature (53/57/62°C). After 10 min. polymerization time, polyvinyl alcohol was fed from a nitrogen pressurized bomb. The standard polymerization time was 8 hours. Before opening of the vessel atmospheric pressure was attained, and the vessel was evacuated for at least half an hour. The Polyvinyl chloride formed was filtered and washed on a glass filter (S2). Subsequently, the polyvinyl chloride was dried in a fluid bed dryer at 60°C.

The results are shown in Table 2.

Table 2 vinyl chloride polymerization with ketone peroxide according to the present invention.

Peroxide	Temp °C	perox %	yield %	CPT Min
Peroxide of example 11	42	0.12	88.2	287
Peroxide of example 11	62	0.090	85.1	335
Peroxide of example 12	62	0.098	98.8	165

% peroxy = mass % on VCM

CPT = constant pressure time: time until vinyl chloride pressure drop (about

75% conversion)

Example 16. In order to determine the cure performance of the peroxy compounds according to the present invention as a curing agent for unsaturated polyester, a comparison was made with a conventional curing agent, tertiary butyl per 2-ethyl hexanoate (conventional compound).

The Time-Temperature curve was measured at 100°C on compounds containing 100 parts of polyester resin, 150 parts of sand as filler, and 1 part of the curing agent. This procedure was carried out according to the method outlined by the Society of Plastic Institute. 25 g of compound were poured into a test tube and a thermocouple was inserted through the enclosure cork in the middle of the tube. The glass tube was then placed in the oil bath maintained at a specific test temperature and the time-temperature curve was measured. From the curve the following parameters were calculated:

Gel time (GT) = time in minutes elapsed between 16.7°C below and 5.6°C above the bath temperature.

Time to peak exotherm (TTP) = time elapsed between the start of the experiment and the moment the peak temperature is reached.

Peak exotherm (PE) = the maximum temperature reached.


The results are summarised in the following table:

COMPOUND	TEST TEMP, °C	GT, MIN.	TTP, MIN.	PE, °C
Tert.butylperoxy 2-ethyl hexanoate	100	0.87	3.4	197
Example 10	100	0.15	2.57	196
Example 3	100	0.2	2.33	190
Example 12	100	0.28	2.35	195

All peroxy compounds according to the present invention showed a faster reactivity in terms of gel time and time to peak.


Claims

1. Process for the preparation of monoperoxy ester or monoperoxy carbonate having the general formula I:



wherein R_1 and R_2 are independently selected from the group comprising hydrogen, C_1 - C_{20} alkyl, C_3 - C_{20} cycloalkyl, C_6 - C_{20} aryl, C_7 - C_{20} aralkyl, and C_7 - C_{20} alkaryl, or R_1 and R_2 form a C_3 - C_{12} cycloalkyl group, which groups may include linear or branched alkyl moieties, and each of R_1 and R_2 may optionally be substituted with one or more groups selected from hydroxy, alkoxy, linear or branched alkyl, aryloxy, halogen, ester, carboxy, nitrile, and amido, and

R_3 is independently selected from the group comprising C_1 - C_{20} alkyl, C_3 - C_{20} cycloalkyl, C_6 - C_{20} aryl, C_7 - C_{20} aralkyl, and C_7 - C_{20} alkaryl, which groups may include linear or branched alkyl moieties, and R_3 may optionally be substituted with one or more groups selected from hydroxy, alkoxy, linear or branched alkyl, aryloxy, halogen, ester, carboxy, nitrile, and amido, which process comprises the reaction of the corresponding ketone peroxide with the general formula II:




wherein R_1 and R_2 have the identified meaning, with a reactive carbonyl compound with the general formula III:



wherein R_3 has the identified meaning and L is a group activating a


carbonyl group of the carbonyl compound (III) for reaction with the ketone peroxide (II), in an inert two-phase solvent system comprising a polar solvent and an apolar solvent.

- 5 2. A process as claimed in claim 1 wherein the equivalent amount of the carbonyl compound is in the range of 0.5-5 equivalents, preferably 1-2 equivalents.
- 10 3. A process as claimed in claim 1 or 2 wherein L is halogen or the group $-O-R_3'$, $-O-CO-R_3'$ or $-O-CO-O-R_3'$ and R_3' is selected independently of R_3 from the same group as R_3 .
- 15 4. A process as claimed in claim 1 or 2 wherein the ketone peroxide is derived from methylethyl ketone, methylisopropyl ketone, methylisobutyl ketone, acetone, cyclohexanone, and/or 2,4,4-trimethylcyclohexanone, preferably from methylisobutyl ketone, and the acid chloride is selected from the group comprising acetyl chloride, 2-ethylhexanoyl chloride, pivaloyl chloride, neodecanoyl chloride, neoheptanoyl chloride, and isobutyryl chloride, or the halogen formate is selected from the group comprising the chloroformates 2-ethylhexanoyl chloroformate, isopropyl chloroformate, sec.butyl chloroformate, ethyl chloroformate, n-butyl chloroformate, n-butyl 4-tert.butyl cyclohexyl chloroformate, tetradecyl chloroformate, hexadecyl chloroformate.
- 20 5. Monoperoxy ester or monoperoxy carbonate having the general formula I



wherein R_1 , R_2 and R_3 have the identified meaning, which is obtainable with the process of claims 1-4.


6. Process for the preparation of the mixed peroxide having the general formula IV:





wherein R₁, R₂, R₅, R₆ and R₇ are independently selected from the group comprising hydrogen, C₁-C₂₀ alkyl, C₃-C₂₀ cycloalkyl, C₆-C₂₀ aryl, C₇-C₂₀ aralkyl, and C₇-C₂₀ alkaryl, or R₁ and R₂ form a C₃-C₁₂ cycloalkyl group, which groups may include linear or branched alkyl moieties, and each of R₁, R₂, R₅, R₆ and R₇ may optionally be substituted with one or more groups selected from hydroxy, alkoxy, linear or branched alkyl, aryloxy, halogen, ester, carboxy, nitrile, and amido;

R₃ and R₄ are independently selected from the group comprising C₁-C₂₀ alkyl, C₃-C₂₀ cycloalkyl, C₆-C₂₀ aryl, C₇-C₂₀ aralkyl, and C₇-C₂₀ alkaryl, which groups may include linear or branched alkyl moieties, and each of R₃ and R₄ may optionally be substituted with one or more groups selected from hydroxy, alkoxy, linear or branched alkyl, aryloxy, halogen, ester, carboxy, nitrile, and amido;

any pair of the optionally substituted R₄, R₅, R₆ and R₇ may form a ring, which process comprises the reaction of the corresponding monoperoxy ester or monoperoxy carbonate with the general formula I:




wherein R₁, R₂, and R₃ have the identified meaning, with an alkyl vinyl ether with the general formula Va or with an acetal with the general formula Vb:



wherein $R_4 - R_7$ have the identified meaning, in the presence of a catalyst.


7. A process as claimed in claim 6 wherein the monoperoxy ester or monoperoxy carbonate is obtainable with the process according to any one of claims 1-4.

8. Mixed peroxide having the general formula IV:




- wherein $R_1, R_2, R_3, R_4, R_5, R_6$ and R_7 have the identified meaning, which is obtainable with the process of claim 6 or 7.

9. A mixed peroxide as claimed in claim 8 wherein R_5, R_6 and/or R_7 are hydrogen.
10. Process for the preparation of a mixed diperoxy ester and a peroxy ester peroxy carbonate having the general formula VI:




- wherein R_1 and R_2 are independently selected from the group comprising hydrogen, C_1 - C_{20} alkyl, C_3 - C_{20} cycloalkyl, C_6 - C_{20} aryl, C_7 - C_{20} aralkyl, and C_7 - C_{20} alkaryl, or R_1 and R_2 form a C_3 - C_{12} cycloalkyl group, which groups may include linear or branched alkyl moieties, and each of R_1 and R_2 may optionally be substituted with one or more groups selected from hydroxy, alkoxy, linear or branched alkyl, aryloxy, halogen, ester, carboxy, nitrile, and amido, and R_3 and R_8 are mutually different and independently selected from the group comprising C_1 - C_{20} alkyl, C_3 - C_{20} cycloalkyl, C_6 - C_{20} aryl, C_7 - C_{20} aralkyl, and C_7 - C_{20} alkaryl, which groups may include linear or

branched alkyl moieties, and each of R_3 and R_8 may optionally be substituted with one or more groups selected from hydroxy, alkoxy, linear or branched alkyl, aryloxy, halogen, ester, carboxy, nitrile, and amido, in which process monoperoxy ester or monoperoxy carbonate with the general formula I:




wherein R_1 , R_2 , and R_3 have the identified meaning, is reacted with a carboxylic acid anhydride with the general formula VII:



wherein R_8 has the identified meaning, in the presence of an acid catalyst.


11. A process as claimed in claim 10 wherein the monoperoxy ester or monoperoxy carbonate is obtainable with the process according to any one of claims 1-4.

12. Mixed diperoxy ester and peroxy ester peroxy carbonate having the general formula VI:




wherein R_1 , R_2 , R_3 , and R_8 have the identified meaning, which is obtainable with the process of claims 10 or 11.


13. Process for the preparation of a mixed diperoxy carbonate having the general formula VIII:



wherein R_1 and R_2 are independently selected from the group comprising hydrogen, C_1 - C_{20} alkyl, C_3 - C_{20} cycloalkyl, C_6 - C_{20} aryl, C_7 - C_{20} aralkyl, and C_7 - C_{20} alkaryl, or R_1 and R_2 form a C_3 - C_{12} cycloalkyl group, which groups may include linear or branched alkyl moieties, and each of R_1 and R_2 may optionally be substituted with one or more groups selected from hydroxy, alkoxy, linear or branched alkyl, aryloxy, halogen, ester, carboxy, nitrile, and amido, and R_3 and R_9 are independently selected from the group comprising C_1 - C_{20} alkyl, C_3 - C_{20} cycloalkyl, C_6 - C_{20} aryl, C_7 - C_{20} aralkyl, and C_7 - C_{20} alkaryl, which groups may include linear or branched alkyl moieties, and R_3 and R_9 may optionally be substituted with one or more groups selected from hydroxy, alkoxy, linear or branched alkyl, aryloxy, halogen, ester, carboxy, nitrile, and amido, which process comprises the reaction of the monoperoxy carbonate with the general formula I':



wherein R_1 and R_2 have the identified meaning, with a halogen formate with the general formula III':




wherein R_9 has the identified meaning with the proviso that R_9 is not identical with R_3 .

14. A process as claimed in claim 13 wherein the identical equivalent amount of halogen formate is in the range of 1-5 equivalents, preferably 3-5 equivalents.

15. A process as claimed in claim 13 or 14 wherein the monoperoxy carbonate is obtainable with the process of claims 1-4.

16. Mixed diperoxy carbonate having the general formula VIII:



wherein R_1 , R_2 , R_3 , and R_9 have the identified meaning, which is obtainable with the process of any one of the claims 13-16.

17. The use of the peroxy esters, peroxy carbonates, mixed diperoxides, mixed peroxy esters, mixed peroxy carbonates, and peroxy ester peroxy carbonates as claimed in claims 1-16 and mixtures thereof as polymerization initiators, curing agents for unsaturated polyester, and modifying agents.

18. Formulation comprising a peroxy ester, peroxy carbonate, mixed diperoxy mixed peroxy esters, mixed peroxy carbonates, and peroxy ester peroxy carbonates, and mixtures thereof as defined in any one of claims 1-16, and a carrier or diluent.

19. A formulation as claimed in claim 18 comprising the peroxy ester, peroxy carbonate, mixed diperoxide mixed peroxy esters, mixed peroxy carbonates and peroxy ester peroxy carbonates and mixtures thereof in an amount of 1.0-99% by wt, preferably 10-90% by wt, more preferably by 30-90% wt, most preferably 40-80% by wt.

20. A formulation as claimed in claim 18 or 19 wherein the carrier or diluent is a solid, liquid, or paste.

21. A formulation as claimed in claims 18-20 wherein the liquid is an apolar

solvent.

22. A formulation as claimed in claims 18-21 having the form of a dispersion, such as a suspension or an emulsion.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 99/02643

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C07C407/00 C07C409/38 C07C409/40 C08F4/36 C08F299/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C07C C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	G.A. RAZUVAEV ET AL.: "Thermal decomposition of bis(1-methylpercarbonatocyclohexyl)peroxides" JOURNAL OF GENERAL CHEMISTRY USSR, vol. 33, 1963, pages 124-130, XP002077296 NEW YORK US page 124 --- -/--	16,17



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- "Z" document member of the same patent family

Date of the actual completion of the international search

16 July 1999

Date of mailing of the international search report

26/07/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Bonnevalle, E

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>A.I. KIRILLOV: "Reactions of free peroxidic alkoxy radicals formed by the decomposition of acylated bis-(2-hydroperoxybutyl) peroxides" JOURNAL OF ORGANIC CHEMISTRY OF THE USSR. (ZHURNAL ORGANICHESKOI KHIMII), vol. 1, no. 7, 1965, pages 1241-1245, XP002077297 NEW YORK US page 1243 - page 1244</p>	1-4
A	<p>YU.A. OL'DEKOP ET AL.: "1,1'-Bis (acylperoxy) dicyclohexyl peroxides" DOKLADY CHEMISTRY., vol. 139, 1961, pages 811-814, XP002077298 NEW YORK US page 811</p>	1-4
A	<p>CHEMICAL ABSTRACTS, vol. 084, no. 8, 23 February 1976 (1976-02-23). Columbus, Ohio, US; abstract no. 044981, YOSHIKAWA K ET AL: "Polymerizing ethylene" XP002077299 cited in the application abstract & JP 50 023079 - (SUMITOMO CHEMICAL CO., LTD.; JAPAN) 5 August 1975 (1975-08-05)</p>	13-16
A	<p>FR 2 376 844 A (PENNWALT CORP) 4 August 1978 (1978-08-04) page 6; claims</p>	1, 17, 18

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 99/02643

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 50023079	-	NONE	
FR 2376844	A	04-08-1978	
		US 4097408 A	27-06-1978
		AU 519894 B	07-01-1982
		AU 2933277 A	12-04-1979
		CA 1096846 A	03-03-1981
		DE 2757440 A	13-07-1978
		GB 1589417 A	13-05-1981
		JP 1414484 C	10-12-1987
		JP 53087308 A	01-08-1978
		JP 62023761 B	25-05-1987
		NL 7800021 A,B	10-07-1978
		US 4129704 A	12-12-1978

